



Epoxy Glass Cloth Sheet EP GC 203

CEI - IEC 60893 Type EP GC 203 (Epoxy resin, glass cloth)

Mechanical Properties				
		Unit	Value	Test Method
	Density	g/cm ³	1,8 - 1,9	ISO 1183
	Glass content	%	65	ISO 1172
	Water absorption	mg	20	ISO 62
	Flexural Strength at 23°C	MPa	450	ISO 178
	Flexural Strength at 150°C	MPa	250	ISO 178
	Flexural Strength at 23°C, after ageing 30 days at 180°C	MPa	500	ISO 178
	Tensile Strength at 23°C	MPa	350	ISO 527
	Compressive strength // to laminations at 23°C	MPa	300	ISO 604
	Impact strength (Charpy) un-notched // to laminations	KJ/m ²	120	ISO 179
	Impact strength (Charpy) notched // to laminations	KJ/m ²	90	ISO 179
	Splitting load	N	5000	DIN 53463
Electrical Properties				
	Insulating resistance between 2 plugs (24h at 23°C Water)	Ω	10 11	IEC 60167

No. 322, Lane 999, Xinsong Rd., Shanghai 201612, China

Tel: 0086-21-57688232

Fax: 0086-21-57688319

Mobile: 0086-1381-6118212

E-mail: stbpi@stbpi.com



Shanghai Technical By-Products Int'l Corp. Co., Ltd.

	Flat-wise electric strength \perp to laminations (3mm), 90°C in oil	KV	40	IEC 60243
	Breakdown voltage // to laminations, 90°C in oil	KV	50	IEC 60243
	Dissipation factor at 1 MHz		0,015	IEC 60250
	Relative permittivity at 1 MHz		4,5	IEC 60250
	Comparative tracking Index	V	500	IEC 60112
Thermal Properties				
	Temperature Index	°C	155	IEC 60216
	Thermal class		F	

RoHS Directive

Hazardous products listed in the EU-directive 2002/95/CE (RoHS) ERS directive are not used as ingredients in this material.

Applications: Used in Electrical Industries for manufacturer of Generators, Transformers, etc.

Availability: In Sheets, tubes, rods or Machined Parts. We specialize in Machined Parts mainly.

No. 322, Lane 999, Xinsong Rd., Shanghai 201612, China
Tel: 0086-21-57688232
Fax: 0086-21-57688319
Mobile: 0086-1381-6118212
E-mail: stbpi@stbpi.com